



SCREENING AND CHARACTERIZATION OF PLASTIC DEGRADING BACTERIA FROM GARBAGE SOIL

Patil R. C*

Department of Microbiology, Bhavan's College, Andheri, Mumbai

ARTICLE INFO

Article History:

Received 8th July, 2017

Received in revised form 9th

August, 2017 Accepted 20th September, 2017

Published online 28th October, 2017

Key words:

Biodegradation, Plastics, Microorganisms, FTIR.

ABSTRACT

In this study, the screening of plastic degrading microbes was done by using opaque method separately for bacteria and fungi. Four bacterial species and two fungal species which formed most opaque were used for further studies. The bacterial species was identified as *Bacillus amylolyticus*, *Bacillus firmus*, *Pseudomonas putida*, *Pseudomonas fluorescens*. Their effectiveness on the degradation of commercial polythene carry bags of Low Density Polyethylene was studied over a period of 30 days in shaker culture under laboratory conditions by weight determination method and it was found that *Bacillus* sp. isolated from Garbage soil degrades the plastic up to 32%. This work reveals that *Bacillus amylolyticus* posses greater potential to degrade plastics when compared with other bacteria.

Copyright©2017 Patil R. C. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

INTRODUCTION

Plastics are non-biodegradable, strong, durable, moisture resistant, light weight polymers of carbon along with hydrogen, nitrogen, sulphur, and other organic and inorganic elements and are manufactured from fossil fuel which is a non-renewable source (Sreedevi *et al.*, 2015). A very general estimate of worldwide plastic waste generation is annually about 57 million tons (Bollag *et al.*, 2000). They do not break down in the environment easily because they are resistant to microbial attack, due to their excessive molecular mass, high number of aromatic rings, unusual bonds, or halogen substitutions (Alexander, 1981). As a result they remain in the environment for a very long time without any deterioration and the large-scale accumulation of waste plastics in the biosphere has given rise to the problem of severe environmental pollution. These problems have made plastic waste a major focus in the management of solid waste. Due to plastic's resilience against degradation and its proliferation in industry, the issue of plastic pollution has evolved to become a threat to global ecology (Kim and Rhee, 2003).

Low density polyethylene (LDPE) is one of the major sources of environmental pollution. Polyethylene is a polymer made of long chain monomers of ethylene. The worldwide utility of polyethylene is expanding at a rate of 12% annum and approximately 140 million tones of synthetic polymers are produced worldwide each year. With such huge amount of

polyethylene getting accumulated in the environment, their disposal evokes a big ecological issue. It takes thousand years for their efficient degradation. Since polymers are extremely stable, their degradation cycles in the biosphere are limited (Shimao, 2001).

Environmental pollution by synthetic polymers, such as waste plastics and water-soluble synthetic polymers in waste-water has been recognized as a major problem. In view of this, energetic, chemical and biological polymer-degrading techniques have been studied extensively during the last three decades. Usage of certain microorganisms and enzymes to degrade polymers are classified as the biodegradation method of polymers (Premraj and Doble, 2005).

The microbial species are associated with the degrading materials. Microbial degradation of plastics is caused by certain enzymatic activities that lead to a chain cleavage of the polymer into oligomers and monomers. These water soluble enzymatically cleaved products are further absorbed by the microbial cells where they are metabolized. Aerobic metabolism results in carbon dioxide and water (Starnecker and Menner, 1996), and anaerobic metabolism results in the production of carbon dioxide, water and methane and are called end products, respectively (Gu *et al.*, 2000). The degradation leads to breaking down of polymers to monomers creating an ease of accumulation by the microbial cells for further degradation (Kumari *et al.*, 2013).

Microorganisms can degrade plastic over 90 genera, from bacteria and fungi, among them; *Bacillus megaterium*, *Pseudomonas* sp., *Azotobacter*, *Ralstonia eutropha*,

*Corresponding author: Patil R. C

Department of Microbiology, Bhavan's College, Andheri, Mumbai

Halomonas sp., etc. (Chee *et al.*, 2010). Plastic degradation by microbes due to the activity of certain enzymes that cause cleavage of the polymer chains into monomers and oligomers. Plastic that has been enzymatically broken down further absorbed by the microbial cells to be metabolized. Aerobic metabolism produces carbon dioxide and water. Instead of anaerobic metabolism produces carbon dioxide, water, and methane as end products (Usha *et al.*, 2011).

The purpose of this study was to isolate microorganism from dumped soil area and screening of the potential plastic degrading microorganisms and indentifying the high potential microorganism that degrade the plastics.

MATERIALS AND METHODS

Sample collection

The Garbage soil sample (Municipal solid waste, where plastic bags were buried) was obtained from a compost plant, Municipal Corporation of Greater Mumbai (MCGM), India. The compost inoculum was free from larger inert materials (glass, stones, metals, etc.) as much as possible. These items are removed manually as much as possible to produce a homogenous compost inoculum. The soil sample had the following basic properties: total solids (%TS) 81%; volatile solids at 550°C (%VS) 18%, pH 7.2, C/N ratio 15.3. It was used for isolation of polymer degrading microorganisms.

Plastic Material: Commonly available plastic bags were collected from Solid waste plant of Municipal Corporation of Greater Mumbai (MCGM).

Media for cultivation and degradation experiments

Nutrient broth and Nutrient agar were obtained from HIMEDIA Laboratories Ltd. Minimal synthetic media includes (NH₄NO₃ (1.0 g/l), MgSO₄.7H₂O (0.2 g/l), K₂HPO₄ (1.0 g/l), CaCl₂.2H₂O (0.1 g/l), KCl (0.15 g/l), Yeast extract (0.1 g/l), FeSO₄.6H₂O (1.0 mg/l), ZnSO₄.7H₂O (1.0 mg/l), MnSO₄ (1.0 mg/l) devoid of any carbon source was used for degradation experiments. Media sterilization was performed by autoclaving at 121°C and 15 lbs pressure for 15 minutes.

Isolation of polymer degrading microorganisms

The plastic degrading microorganisms were isolated from soil with the help of serial dilution.

Total heterotrophic count

C.F.U. /g= Number of colonies/ inoculums size (ml) X dilution factor

Bacterial isolation and identification

The bacterial strains isolated with the ability to degrade and performed on the basis of macroscopic and microscopic examination and biochemical test. The bacterial isolates were identified macroscopically by examining colony by examining colony morphology, surface pigment, size shape, margin, surface on media plates and microscopic examination including, grams staining to study the staining behavior, shape, and cell arrangement and granulation, spore staining. The motility test was also per performed biochemical test. The isolates were identified by using selective medium (Kandler and Weiss, 1986).

Microbial Degradation of Plastics in Laboratory Condition

Determination of Weight Loss

Pre-weighed discs of 1-cm diameter prepared from polythene bags were aseptically transferred to the conical flask containing 50 ml of culture broth medium, inoculated with different bacterial species. Control was maintained with plastic discs in the microbe-free medium. Different flasks were maintained for each treatment and left in a shaker. After one month of shaking, the plastic discs were collected, washed thoroughly using distilled water, shade-dried and then weighed for final weight. From the data collected, weight loss of the plastics was calculated.

Fourier Transform Infrared (FTIR) and Attenuated Total Reflectance (ATR) spectroscopy

FTIR analysis is a useful tool to determine the formation of new or disappearance of functional groups. So degradation products, chemical moieties incorporated into the polymer molecules such as branches, co-monomers, unsaturation and presence of additives such as antioxidants can be determined by this technique. Fourier transform-attenuated total reflectance (FT-ATR) infrared spectroscopic studies were carried out on plastic samples using a Shimadzu in the horizontal ATR mode, using a zinc-selenide crystal. A total of 3 scans were taken.

RESULTS AND DISCUSSION

The present study aimed to degrade the plastic strips using microbes isolated from Garbage soil samples. Many different bacterial and fungal isolates were obtained from the soil samples. But only three predominant bacterial colonies and fungal colonies were chosen by screening and they were identified based on their Morphological and biochemical characteristics.

Probable identification of isolates		
Sr. No.	Isolates	Identified isolate
1.	Isolate 1	<i>Bacillus amylolyticus</i>
2.	Isolate 2	<i>Bacillus subtilis</i>
3.	Isolate 3	<i>Pseudomonas putida</i>
4.	Isolate 4	<i>Pseudomonas fluorescense</i>

The bacterial strains isolated with the ability to degrade and performed on the basis of macroscopic and microscopic examination and biochemical test. The bacterial isolates were identified macroscopically by examining colony characteristics, pigment, size shape, margin, and microscopic examination including, grams staining to study the staining behavior, shape, and cell arrangement and granulation, spore staining, motility test was also per performed biochemical test.

A total of four isolates were isolated from dumped soil of Municipal Corporation of Mumbai. These four isolates were purified in order to tilt to the next test and screened for plastic degradation by incubation for 1 month in an incubator shaker at 130 rpm agitation in a 37°C temperature conditions. The bacteria which were identified from the above biochemical tests are *Bacillus amylolyticus*, *Bacillus subtilis*, *Pseudomonas putida* and *Pseudomonas fluorescense*, by the software PIBWIN (Probabilistic identification of bacteria).

Degradation of Polyethylene Plastic Waste was carried out (Kathiresan, 2003). Weigh polyethylene plastic (initial weight) and then washed with sterile distilled water and

Screening And Characterization of Plastic Degrading Bacteria From Garbage Soil

sprayed with 70% alcohol. Plastic is inserted into the 100 mL erlenmeyer containing NB and TSB media as much as 50 mL aseptically. So as much as 2 loops inoculated bacterial isolates to the media. Then incubated in an incubator shaker at room temperature, with agitation of 130 rpm for a month. Polyethylene plastic that has been incubated for a month, washed with sterile distilled water and then sprayed with alcohol dried aired then weighed (final weight). Determination of the percentage of degradation of polyethylene plastic by bacteria by using following formula:

$$\% \text{Degradation} = \frac{\text{Final weight}}{\text{Initial weight}} \times 100\%$$

Table No. 1 Result of degradation of plastic sample by bacteria

Isolates no.	Name of bacteria	Initial weight (mg)	Final weight (mg)	Total loss in weight (mg)	Weight Loss/month (in %)
1	<i>Bacillus amylolyticus</i>	50	34	16	32
2	<i>Pseudomonas putida</i>	50	41	09	18
3	<i>Pseudomonas fluorescense</i>	50	39	11	22
4	<i>Bacillus subtilis</i>	50	43	07	14

Microbial degradation of plastics under laboratory conditions

To assess this, the pre-weighed discs of 1-cm diameter prepared from polythene bags were aseptically transferred to the conical flask containing 50 ml of culture broth medium, inoculated with different bacterial species separately. Control was maintained with plastic discs in the microbe-free medium. Five flasks were maintained for each treatment and left in a shaker. After one month of shaking, the plastic discs were collected, washed thoroughly using distilled water, shade-dried and then weighed for final weight. From the data collected, weight loss of the polythene bag was calculated. The species tested were *Bacillus amylolyticus*, *Pseudomonas putida*, *Pseudomonas fluorescense* and *Bacillus subtilis*. Among the bacteria, *Pseudomonas putida* and *Bacillus subtilis* were found most active in degrading 30%, and 22 % of polythene respectively in one month period.

FTIR spectra of polyethylene film before and after degradation in compost and in media

Fourier Transform Infrared Spectroscopy analysis was used for detecting the formation of new functional groups or changes in the amount of existing functional groups (Milstein *et al.*, 1994).

FTIR spectra of plastic material. Figure 1 and 2 and 3 shows the FTIR spectra of plastic material after degradation by isolated bacterial strain.




Fig 1 FTIR spectra of plastic before degradation

The overlapping spectra in the expanded form are also provided for comparison, which clearly depict the changes observed. Figure 1 shows the degradation of plastic in synthetic media by bacteria. Plastic strips which were buried in soil were collected and added in synthetic medium containing bacterial species *P. putida* followed by *Bacillus subtilis*, *Bacillus amylolyticus*, *Pseudomonas fluorescense* which are found less plastic degrader as an extra decomposer, that soil combination was a simulation of landfills. Weight losses of polymer strips in medium could be assumed as an indicator of biodegradation in the landfills or natural environment. Soil microorganisms attacked the polymer strips.




Fig 2 FTIR spectra of plastic after degradation by *Bacillus amylolyticus*




Fig 3 FTIR spectra of plastic after degradation by *Pseudomonas fluorescense*

First of all, microorganisms were attracted to the plastic material as source of carbon. Microorganisms consumed plastic in the polymer matrix and caused a fracture in the LDPE chain. FTIR exhibited some change in plastic, after degradation by bacteria. The highest decrease in spectrum was observed at 1500 cm⁻¹ derived from carbonyl groups of potato starches. This reduction confirmed the degradation of plastic in soil. Absorption band was between 1340- 1354 cm⁻¹ because of the weak hydrogen bond between starch and glycerol. Absorption band between 1340 and 1354 cm⁻¹ was derived from C-O-H stretching bond. Alcohol absorption band was 987–1039 cm⁻¹ and this indicated a fast degradation rate of carbon chain (Labuzek *et al.*, 2004). The isolated microbes were native to the site of polyethylene disposal and might show some degradability in natural conditions, yet they also exhibited biodegradation in laboratory conditions on synthetic media. This gives some suggestion that these

microbes can be used in both natural and artificial conditions for the purpose of degradation of polymers. Our knowledge, microbes cause greatest degradation of polythene and plastics. Among the bacteria, viz *Pseudomonas putida* followed by *Bacillus subtilis*, *Bacillus amylophilus* *Bacillus firmus*, *Pseudomonas fluorescens*, having greater degradation ability. It is concluded that isolated strains are solely dependent on plastic for its carbon source. FTIR spectra also confirm the biodegradation of polymer as some chemical changes are seen in surface of polymer. Hence, the further attention is required from microbiologists for commercial degradation and eco-friendly polyethylene.

CONCLUSION

A total of four bacterial strains capable of degrading plastic have been isolated from dumped soil. The isolates obtained were subjected to standard biochemical test results showed the presence of *Pseudomonas sp.*, and *Bacillus sp.* for bacteria. The organisms identified was further inoculated into different culture media and their biodegradative ability was determined by loss of weight after a period of 30 days and observed that bacterial *sp.* degrades up to 32% . Thus it may take 30 days complete degradation of plastics by using bacteria for complete degradation of plastic. Further biochemical test can be done to identify the exact bacterial. Further characterization of the obtained microbes can be done to increase the level of biodegradation of plastic.

References

- Alexander M., Biodegradation of chemicals of environmental concern. *Sci. 211*, 1981, 132-138.
- Bollag, W.B., Jerzy Dec & Bollag, J.M. (2000) Biodegradation & encyclopedia of microbiology. In Lederberg, J (ed.). Academic, New York. 461-471.
- Chee JY, Yoga SS, Lau NS, Ling SC, Abed RMM and Sudesh KL (2010). Bacterially Produced Polyhydroxyalkanoate (PHA): Converting Renewable Resources into Bioplastics, edited by Mendez Vilas A. *Applied Microbiology and Biotechnology*.
- Gu, J.D., Ford, T.E., Mitton, D.B. and Mitchel, R. (2000) Microbial corrosion of metals. W. Revie (Ed.), The Uhlig Corrosion Handbook (2nd Edition), Wiley, New York .915-927.
- Kandler, O. and Weiss, N. (1986) Regular non-sporing Gram positive rods. In Bergey's Manual of Systematic Bacteriology ed. Krieg, N.R. and Holt, J.G. pp. 1209–1234. Baltimore: Williams & Wilkins
- Kathiresan K. (2003). Polythene and Plastics-degrading microbes from the mangrove soil, *Rev. Biol. Trop.*, 51(3), 629-634.
- Kim D. Y., H. Y. Rhee, Biodegradation of microbial and synthetic polyesters by fungi. *Appl Microbiol Biotechnol.* 61, 2003, 300-308.
- Kumari N.A., Kumari P. and Murthy N.S.(2013). A Novel Mathematical Approach for Optimization of Plastic Degradation, *Int. J. Engg. Trends and Tech.*, 4(8), 3539- 3542.
- Milstein, O., R. Gersonde, A. Huttermann, R. Frund, H. J. Feine, H. D. Ludermann, M. J. Chen, and J. J. Meister. 1994. Infrared and nuclear magnetic resonance evidence of degradation in thermoplastics based on forest products. *J. Environ. Polym. Degrad.* 2(2): 137-152.
- Premraj R., M. Doble, Biodegradation of Polymers, *Ind. J. Biotechnol.* 4, 2005, 186-193.
- Shimao, M. (2001) biodegradation of plastics. *Curr. Opin. Biotechnol.* 12: 242-247.
- Sreedevi S. (2015). Solid Waste Generation and its Management- A Case Study, *Int. Res. J. Environment Sci.*, 4(1), 90-93
- Starnecker, A. and M. Menner, 1996. Assessment of biodegradability of plastics under stimulated composting conditions in a laboratory test system. *International biodeterioration and Biodegradation*, pp: 85-92.
- Usha R, Sangeetha T and Palaniswamy M (2011). Screening of Polyethylene Degrading Microorganisms from Garbage Soil. *Libyan Agricultural Research Center Journal International* 2(4) 200-204.

How to cite this article:

Patil R. C (2017) 'Screening And Characterization of Plastic Degrading Bacteria From Garbage Soil', *International Journal of Current Advanced Research*, 06(10), pp. 6414-6417. DOI: <http://dx.doi.org/10.24327/ijcar.2017.6417.0937>
